

测试报告

No. SHAHG1100832402

日期: 2011年01月25日 第1页,共2页

青岛银圭新材料科技有限公司

青岛市海尔路61号天宝国际2号楼2009室

以下测试之样品是由申请者所提供及确认: 银圭涂料

SGS工作编号: SHD201101642 - SH

样品接收日期: 2011年01月19日

测试周期: 2011年01月19日 - 2011年01月25日

测试要求: 根据客户要求测试

测试方法: 请参见下一页

测试结果: 请参见下一页

结论: 使用了银圭涂料的所测试样品金属锅内带白色涂层符合FDA对树脂及聚合物涂层提取物的含量要求。

通标标准技术服务有限公司

授权签名

Crystal Zhou

Zhou Yan, Crystal 周燕

批准签署人

本报告是发布日期为2011年01月25日编号为SHAHG1100832401 英文检测报告的中文译本。如有异议, 以英文版本为准。

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.



3rd Building, No. 889 Yishan Road Xuhui District, Shanghai China 200233
中国·上海·徐汇区宜山路889号3号楼 邮编: 200233

t E&E (86-21) 61402553 f E&E (86-21) 64953679 www.cn.sgs.com
HL: (86-21) 61402594 HL: (86-21) 54500353 e sgs.china@sgs.com

Member of the SGS Group (SGS SA)

测试报告

No. SHAHG1100832402

日期: 2011年01月25日 第2页,共2页

测试结果:

样品部件外观描述:

样品编号	SGS样品ID	描述
1	SHA11-008324.001	金属锅内带白色涂层

FDA 21CFR 175.300

测试方法: 按照FDA 21 CFR 175.300 规定.

常用模拟液	时间	温度	最大允许限值	样品001 提取物(总量)
蒸馏水	2.0hr	250°F	18mg/inch ²	<0.1mg/inch ²
正庚烷	2.0hr	150°F	18mg/inch ²	0.2mg/inch ²

样品照片:



此照片仅限于随SGS正本报告使用

*** 报告完 ***

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.